

weberkol seraçım max

Cement based tile adhesive with reduced slip

Technical Data Sheet:

Issued on 23.11.2022

Revision No: 013

■ Description

Cement based tile adhesive with reduced slip.

■ Reference standards

- TS EN 12004/CIT class
- CE
- Public Works Pos No: 10.300.2201
- Please see current "weber solution guide" for the classification introduced by TS EN 12004 norm about tile adhesives.

■ Advantages

- Easy application
- Safe use in tile application
- Safe use in the construction of aerated concrete

■ Range of application

•Used for fixing ceramic, tile and similar coating materials on interior walls, floors. Bonding of aerated concrete and any other high water absorbing construction elements.

■ Application substrates

•Interior walls:

•Cement based render;

•Interior floors;

•Cement based screed,

•Concrete floor,

•Please see current "weber solution guide" "product section tables for substrate types and max. coating sizes to be applied with **weberkol seraçım max**.

•Please consult us for all other application substrates.

■ Preparation of substrates

- The surface should be dry, smooth and durable. Plasters thinner than 3 mm on the substrate should be scraped and cleaned thoroughly.
- Porous substrates should be wetted. Wait until the water layer disappears as the floor will remain damp.
- Important deformations or holes on the substrate should be repaired with **weberrep** structural repair mortars minimum 24 hours before the application of **weberkol seraçım max**
- Local repairs thinner than 7 mm can be done by use of **weberkol seraçım max**.

■ Conditions of application

- Ambient temperature is between +5 °C and +35 °C.
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.
- Avoid application under direct sunlight, strong wind or hot surfaces.
- Avoid film formation by **weberkol seraçım max** during application, if film is present, that area should be notched again.

■ Application

- Average 6,75-7 lt. water and preferably 25 kg kraft bag **weberkol seraçım max** should be mixed with low- speed mixer preferably or trowel until no more lump will remain.
- After aging **weberkol seraçım max** for 5 minutes, it should be mixed for further 1-2 minutes before application.
- The mortar should be applied on the substrate and its thickness should be adjusted with steel notched trowel. Tooth size of trowel should be adjusted according to dimensions of tile and smoothness of application substrate.
- Mortar should be applied on both application substrate and backside of tiles consumption table mentioned size (double-sided adhesion).
- **Interior floor applications:**
- Tiles bigger than 1100 cm²
- **Interior wall applications:**
- Tiles bigger than 500 cm²
- For good adhesion force should be applied by means of rubber hammer and air should be ejected.
- In application, weight of the coating is a important as the size

■ Application tools

Hand mixer, trowel, rubber hammer, steel notched trowel.

■ Consumption

weberkol seraçım max	4-6 kg/m ²
-----------------------------	-----------------------

■ Attention points

- This product is not used on metal surface floors subject to heavy traffic, prefabricated and underfloor heated floors, old painted surfaces, swimming pools, existing ceramic coating, gross concrete, plasterboards walls, surfaces exposed to climatic changes and subjected to difficult conditions and on terraces and outdoors that will be directly contact with the sun.
- 'C2' class ceramic tile should be used in applications on plaster pannel.
- Never add foreign materials.
- Attention should be paid to the proportion of water that is written on the bag.
- Adding too much or too little water to the product reduces the performance of the product
- All tools are used after application should be washed

The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.

, Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.

■ Technical Information

Product	weberkol seraçım max
Product Type	Powder
Colour	Grey and White
Packaging	25 kg kraft bag (64 bags in pallet, 1600 kg).
Application features	
Pot life	Max 4 hours
Open time	Max 20 minutes
Adjustability	Max 15 minutes
Time required for grouting	24 hours (wall), 48 hours (floor)
Time required for foot traffic	24-48 hours
Application thickness	3 to 10 mm (one or both sides)
Performance	
Fire response class	A1
Initial tensile adhesion strength	$\geq 0,5\text{N/mm}^2$
Tensile adhesion strength after water immersion	$\geq 0,5\text{N/mm}^2$
Tensile adhesion strength after heat aging	$\geq 0,5\text{N/mm}^2$
Tensile adhesion strength after freeze-thaw cycles	$\geq 0,5\text{N/mm}^2$
Open time tensile adhesion strength(after not less than 20 min.)	$\geq 0,5\text{N/mm}^2$
Slip	$\leq 0,5 \text{ mm}$
Heat resistance	between -15°C and $+70^\circ\text{C}$.

■ Storage

Packaging	• 25 kg kraft bag (64 bags in pallet, 1600 kg).
Shelf life	• 1 year as of the production date in dry and moisture- free environment provided that packages will not be opened. • Package should be kept tightly closed when not in use. Package should be protected against frost.

■ Safety Precautions

- Use the appropriate safety equipment (dust mask, gloves).
- Protect your eyes / face.
- Avoid contact with eyes and skin.
- In case of contact with eyes, rinse immediately with plenty of water and consult a specialist.
- Read the Material Safety Data Sheet for more detailed

Legal Warning

Since there are different conditions and requirements that apply in any case, Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş. cannot be liable for other than the information provided in this product datasheet.

These values were obtained as a result of laboratory tests and they are valid for 28 days performance of finished applications. Values may vary due to differences on job-sites.

The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures. Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.